

Gas Permeability - Tedlar® PVF

Properties	Typical Value	Test Method	Test Condition
Carbon dioxide	182 cm ² /m ³ (Std.) atm μ	ASTM-D-1434-75	23.5°C
Helium	23300 cm ² /m ³ (Std.) atm μ	ASTM-D-1434-75	23.5°C
Hydrogen	15600 cm ² /m ³ (Std.) atm μ	ASTM-D-1434-75	23.5°C
Nitrogen	4.1 cm ² /m ³ (Std.) atm μ	ASTM-D-1434-75	23.5°C
Oxygen	52.4 cm ² /m ³ (Std.) atm μ	ASTM D-3985-80	23.5°C

Tedlar® PVF is the registered trademark of Du Pont de Nemours