



Fluoropolymers Outgassing

OUTGASSING: TEMP 125°C TIME 24 HOURS, VACUUM 10⁻⁵ TORR, RH =65%

REQUIREMENTS:

- MAX WL % (WEIGHT LOSS) >1%
- MAX VCMW % (VOLATILE CONDENSABLE MATERIAL WEIGHT) >0.1%

MATERIAL	WL%	VCMW %
PTFE	0.02%	0.02%
FEP	0.04%	0.05%
ETFE	0.07%	0.01%

For more information about our products and services, please visit adtech.co.uk.

For technical assistance, contact our customer service team:

+44 (0)1285 762000 - sales@adtech.co.uk